

Classifications

EN ISO 3581-A	EN ISO 3581-B	AWS A5.4 / SFA-5.4
E 23 12 2 L R 3 2	ES309LMo-17	E309LMo-17

Characteristics and typical fields of application

Rutile coated electrode of E 23 12 2 L / E309LMo-17 type. Provides increased delta ferrite content (FN ~20) in the weld metal for safe and crack resistant dissimilar joints as well as for cladding or root passes of clad steel. Designed for first class weld seams and easy handling on AC or DC+. High current carrying capacity with minimum spatter formation. Self-releasing slag, smooth and clean weld profile. Safety against formation of porosity due to moisture resistant coating and its packaging into hermetically sealed tins. Operating temperature from -60°C to 300°C and for weld surfacing (1st layer) up to 400°C.

Base materials

For the first layer of corrosion resistant surfacing on P235G1TH, P255G1TH, S255N, P295GH, S355N – S500N
 For the first layer of corrosion resistant weld claddings on high temperature quenched and tempered fine-grained steels
 Dissimilar welding of mild steels and low-alloyed construction and QT-steels; unalloyed as well as low-alloyed boiler or constructional steels with stainless Cr-, CrNi- and CrNiMo-steels; ferritic-austenitic welds in boiler and pressure vessel parts

Typical analysis


	C	Si	Mn	Cr	Ni	Mo
wt.-%	0.02	0.7	0.8	23.0	12.5	2.7

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength $R_{p0.2}$	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact energy ISO-V KV J	
	MPa	MPa	%	20°C	-60°C
u	540 (≥ 350)	690 (≥ 550)	28 (≥ 25)	50	40 (≥ 32)

u untreated, as-welded

Operating data

	Polarity	DC+ / AC	Dimension mm	Current A	
	Electrode identification	FOX CN 23/12 Mo-A / E 23 12	2 L R	2.0 × 300	45 – 60
		2.5 × 350		60 – 80	
		3.2 × 350		80 – 120	
		4.0 × 350		100 – 160	
		5.0 × 450		140 – 220	

Preheating and interpass temperature as required by the base metal.
 Redrying at 250 – 300°C for min. 2 h if necessary.

Approvals

TÜV (01362), DB (30.014.41), ABS, RINA, DNV, BV, LR, CE